

Dielectric Constant (DK) / Dissipation Factor (DF) Table

Core Data

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)					
				100 MHz	500 MHz	1 Ghz	2 GHz	5 GHz	10 GHz
106 x 1	71.00%	0.002	0.050	3.90 0.0172	3.83 0.0177	3.83 0.0182	3.81 0.0195	3.75 0.0211	3.74 0.0218
1080 x 1	58.00%	0.0025	0.064	4.12 0.0155	4.05 0.016	4.05 0.0166	4.01 0.0175	3.96 0.019	3.94 0.0198
1080 x 1	64.00%	0.003	0.075	4.01 0.0163	3.93 0.0168	3.93 0.0173	3.90 0.0184	3.85 0.02	3.84 0.0207
106 x 2	63.00%	0.003	0.075	4.02 0.0162	3.95 0.0167	3.95 0.0172	3.92 0.0183	3.86 0.0198	3.85 0.0206
2113 x 1	52.00%	0.0035	0.089	4.27 0.0147	4.20 0.0153	4.20 0.0158	4.15 0.0166	4.11 0.0181	4.08 0.0189
3313 x 1	50.00%	0.0035	0.089	4.32 0.0145	4.26 0.015	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
106 x 2	67.00%	0.0035	0.089	3.96 0.0167	3.88 0.0172	3.88 0.0177	3.85 0.0189	3.80 0.0205	3.79 0.0212
2113 x 1	57.00%	0.004	0.100	4.15 0.0154	4.08 0.0159	4.08 0.0164	4.03 0.0173	3.99 0.0189	3.97 0.0197
3313 x 1	55.00%	0.004	0.100	4.19 0.0151	4.12 0.0156	4.12 0.0162	4.08 0.017	4.03 0.0185	4.01 0.0194
106 x 2	71.00%	0.004	0.100	3.90 0.0172	3.83 0.0177	3.83 0.0182	3.81 0.0195	3.75 0.0211	3.74 0.0218
2116 x 1	50.00%	0.0045	0.114	4.32 0.0145	4.26 0.015	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
1080 x 2	55.00%	0.0045	0.114	4.19 0.0151	4.12 0.0156	4.12 0.0162	4.08 0.017	4.03 0.0185	4.01 0.0194

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)					
				100 MHz	500 MHz	1 Ghz	2 GHz	5 GHz	10 GHz
1652 x 1	43.00%	0.005	0.125	4.53 0.0135	4.48 0.0141	4.47 0.0147	4.42 0.0152	4.39 0.0166	4.34 0.0175
2116 x 1	54.00%	0.005	0.125	4.22 0.015	4.15 0.0155	4.15 0.0161	4.10 0.0169	4.06 0.0184	4.03 0.0192
1080 x 2	58.00%	0.005	0.125	4.12 0.0155	4.05 0.016	4.05 0.0166	4.01 0.0175	3.96 0.019	3.94 0.0198
1652 x 1	47.00%	0.0055	0.140	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
1501 x 1	43.00%	0.006	0.150	4.53 0.0135	4.48 0.0141	4.47 0.0147	4.42 0.0152	4.39 0.0166	4.34 0.0175
1080 x 2	64.00%	0.006	0.150	4.01 0.0163	3.93 0.0168	3.93 0.0173	3.90 0.0184	3.85 0.02	3.84 0.0207
1501 x 1	47.00%	0.0065	0.165	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
7628L x 1	41.00%	0.007	0.175	4.60 0.0133	4.55 0.0138	4.54 0.0144	4.49 0.0148	4.46 0.0163	4.41 0.0172
2113 x 2	52.00%	0.007	0.175	4.27 0.0147	4.20 0.0153	4.20 0.0158	4.15 0.0166	4.11 0.0181	4.08 0.0189
7628L(HRC) x 1	44.00%	0.0075	0.190	4.50 0.0137	4.45 0.0142	4.44 0.0148	4.39 0.0153	4.35 0.0168	4.31 0.0177
7628L(SRC) x 1	47.00%	0.008	0.200	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
7628M x 1	46.00%	0.008	0.200	4.44 0.0139	4.38 0.0145	4.37 0.015	4.33 0.0156	4.29 0.0171	4.25 0.018
3313 x 2	55.00%	0.008	0.200	4.19 0.0151	4.12 0.0156	4.12 0.0162	4.08 0.017	4.03 0.0185	4.01 0.0194
7628M(HRC) x 1	48.00%	0.0085	0.215	4.38 0.0142	4.32 0.0147	4.31 0.0153	4.27 0.0159	4.22 0.0174	4.19 0.0183
2116 x 2	50.00%	0.009	0.225	4.32 0.0145	4.26 0.015	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
1652 x 2	43.00%	0.01	0.250	4.53 0.0135	4.48 0.0141	4.47 0.0147	4.42 0.0152	4.39 0.0166	4.34 0.0175

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)					
				100 MHz	500 MHz	1 GHz	2 GHz	5 GHz	10 GHz
2116 x 2	54.00%	0.01	0.250	4.22 0.015	4.15 0.0155	4.15 0.0161	4.10 0.0169	4.06 0.0184	4.03 0.0192
1652 x 2	47.00%	0.011	0.280	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
1501 x 2	43.00%	0.012	0.300	4.53 0.0135	4.48 0.0141	4.47 0.0147	4.42 0.0152	4.39 0.0166	4.34 0.0175
1501 x 2	47.00%	0.013	0.330	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
7628L x 2	41.00%	0.014	0.360	4.60 0.0133	4.55 0.0138	4.54 0.0144	4.49 0.0148	4.46 0.0163	4.41 0.0172
7628L (HRC) x 2	44.00%	0.015	0.380	4.50 0.0137	4.45 0.0142	4.44 0.0148	4.39 0.0153	4.35 0.0168	4.31 0.0177
7628M x 2	46.00%	0.016	0.410	4.44 0.0139	4.38 0.0145	4.37 0.015	4.33 0.0156	4.29 0.0171	4.25 0.018
7628M x 2 + 1080 x 1	52.00%	0.018	0.460	4.27 0.0147	4.20 0.0153	4.20 0.0158	4.15 0.0166	4.11 0.0181	4.08 0.0189
7628M x 2 + 2116 x 1	47.30%	0.02	0.500	4.40 0.0141	4.34 0.0147	4.33 0.0152	4.29 0.0158	4.24 0.0173	4.21 0.0182
7628L x 3	41.00%	0.021	0.540	4.60 0.0133	4.55 0.0138	4.54 0.0144	4.49 0.0148	4.46 0.0163	4.41 0.0172
7628L x 3	44.00%	0.022	0.558	4.50 0.0137	4.45 0.0142	4.44 0.0148	4.39 0.0153	4.35 0.0168	4.31 0.0177
7628L(SRC) x 3	47.00%	0.024	0.610	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
7628M x 3	46.00%	0.024	0.610	4.44 0.0139	4.38 0.0145	4.37 0.015	4.33 0.0156	4.29 0.0171	4.25 0.018
7628L x 3 + 1080 x 2	50.20%	0.026	0.660	4.32 0.0145	4.25 0.015	4.25 0.0156	4.20 0.0163	4.16 0.0178	4.13 0.0186
7628L x 2 + 7628L (HRC) x 2	42.50%	0.028	0.710	4.55 0.0135	4.50 0.014	4.49 0.0146	4.44 0.0151	4.40 0.0166	4.36 0.0175
7628L(HRC) x 2 + 7628M x 2	45.00%	0.03	0.760	4.47 0.0138	4.41 0.0144	4.40 0.0149	4.36 0.0155	4.32 0.017	4.28 0.0178

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)					
				100 MHz	500 MHz	1 GHz	2 GHz	5 GHz	10 GHz
7628M x 2 + 7628M (HRC) x 2	47.00%	0.032	0.810	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
7628L(HRC) x 4 + 7628L x 1	43.40%	0.035	0.890	4.52 0.0136	4.47 0.0142	4.46 0.0147	4.41 0.0152	4.37 0.0167	4.33 0.0176
7628L x 3 + 7628M x 2	43.00%	0.036	0.914	4.53 0.0135	4.48 0.0141	4.47 0.0147	4.42 0.0152	4.39 0.0166	4.34 0.0175
7628M x 5	46.00%	0.039	1.000	4.44 0.0139	4.38 0.0145	4.37 0.015	4.33 0.0156	4.29 0.0171	4.25 0.018
7628L x 6	41.00%	0.042	1.060	4.60 0.0133	4.55 0.0138	4.54 0.0144	4.49 0.0148	4.46 0.0163	4.41 0.0172
7628L(HRC) x 2 + 7628M x 4	45.30%	0.045	1.140	4.46 0.0138	4.40 0.0144	4.39 0.015	4.35 0.0155	4.31 0.017	4.27 0.0179
7628M x 4 + 7628M(HRC) x 2	46.70%	0.047	1.200	4.42 0.014	4.36 0.0146	4.35 0.0151	4.31 0.0157	4.27 0.0172	4.23 0.0181
7628L(HRC) x 4 + 7628M x 3	44.90%	0.052	1.320	4.47 0.0138	4.42 0.0143	4.41 0.0149	4.36 0.0154	4.32 0.0169	4.28 0.0178
7628M x 7	46.00%	0.055	1.400	4.44 0.0139	4.38 0.0145	4.37 0.015	4.33 0.0156	4.29 0.0171	4.25 0.018
7628L x 4 + 7628M x 4	43.50%	0.059	1.500	4.52 0.0136	4.46 0.0142	4.45 0.0147	4.41 0.0152	4.37 0.0167	4.33 0.0176
7628M x 8	46.00%	0.062	1.570	4.44 0.0139	4.38 0.0145	4.37 0.015	4.33 0.0156	4.29 0.0171	4.25 0.018

Dielectric Constant (DK) / Dissipation Factor (DF) Table

Prepreg Data

Glass Style	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)					
				100 MHz	500 MHz	1 GHz	2 GHz	5 GHz	10 GHz
106	71%	0.0020	0.050	3.90 0.0172	3.83 0.0177	3.83 0.0182	3.81 0.0195	3.75 0.0211	3.74 0.0218
106	76%	0.0025	0.064	3.85 0.0179	3.78 0.0183	3.77 0.0189	3.76 0.0203	3.70 0.0219	3.70 0.0226
1067	71%	0.0025	0.064	3.90 0.0172	3.83 0.0177	3.83 0.0182	3.81 0.0195	3.75 0.0211	3.74 0.0218
1080	64%	0.0030	0.075	4.01 0.0163	3.93 0.0168	3.93 0.0173	3.90 0.0184	3.85 0.0200	3.84 0.0207
1080	68%	0.0035	0.089	3.94 0.0168	3.87 0.0173	3.87 0.0178	3.84 0.0191	3.78 0.0206	3.78 0.0213
1080	72%	0.0040	0.100	3.89 0.0173	3.82 0.0178	3.81 0.0183	3.80 0.0197	3.73 0.0212	3.73 0.0219
1080	75%	0.0045	0.114	3.86 0.0177	3.78 0.0182	3.78 0.0187	3.77 0.0202	3.71 0.0217	3.71 0.0224
2113	52%	0.0035	0.089	4.27 0.0147	4.20 0.0153	4.20 0.0158	4.15 0.0166	4.11 0.0181	4.08 0.0189
2113	57%	0.0040	0.100	4.15 0.0154	4.08 0.0159	4.08 0.0164	4.03 0.0173	3.99 0.0189	3.97 0.0197
2113	61%	0.0045	0.114	4.06 0.0159	3.99 0.0164	3.99 0.0169	3.95 0.0180	3.90 0.0195	3.89 0.0203
3313	50%	0.0035	0.089	4.32 0.0145	4.26 0.0150	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
3313	55%	0.0040	0.100	4.19 0.0151	4.12 0.0156	4.12 0.0162	4.08 0.0170	4.03 0.0185	4.01 0.0194

Glass Style	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)					
				100 MHz	500 MHz	1 GHz	2 GHz	5 GHz	10 GHz
3313	59%	0.0045	0.114	4.10 0.0156	4.03 0.0162	4.03 0.0167	3.99 0.0177	3.94 0.0192	3.92 0.0200
2116	50%	0.0045	0.114	4.32 0.0145	4.26 0.0150	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
2116	54%	0.0050	0.125	4.22 0.0150	4.15 0.0155	4.15 0.0161	4.10 0.0169	4.06 0.0184	4.03 0.0192
2116	58%	0.0055	0.140	4.12 0.0155	4.05 0.0160	4.05 0.0166	4.01 0.0175	3.96 0.0190	3.94 0.0198
1652	47%	0.0055	0.140	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
1652	51%	0.0060	0.150	4.29 0.0146	4.23 0.0151	4.23 0.0157	4.18 0.0164	4.14 0.0179	4.11 0.0188
1501	47%	0.0065	0.165	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
1501	50%	0.0070	0.175	4.32 0.0145	4.26 0.0150	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
7628L	41%	0.0070	0.175	4.60 0.0133	4.55 0.0138	4.54 0.0144	4.49 0.0148	4.46 0.0163	4.41 0.0172
7628L	44%	0.0075	0.190	4.50 0.0137	4.45 0.0142	4.44 0.0148	4.39 0.0153	4.35 0.0168	4.31 0.0177
7628L	47%	0.0080	0.200	4.41 0.0141	4.35 0.0146	4.34 0.0152	4.30 0.0158	4.25 0.0173	4.22 0.0181
7628L	50%	0.0085	0.216	4.32 0.0145	4.26 0.0150	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186
7628M	48%	0.0085	0.215	4.38 0.0142	4.32 0.0147	4.31 0.0153	4.27 0.0159	4.22 0.0174	4.19 0.0183
7628M	50%	0.0090	0.225	4.32 0.0145	4.26 0.0150	4.25 0.0156	4.21 0.0163	4.17 0.0178	4.13 0.0186

NOTE

Please Contact us for more details in below details.

Isola Group 3100 West Ray Road

Suite 301

Chandler, AZ 85226

Phone: 480-893-6527

Phone: 800-537-7656

Fax: 480-893-1409