

Dielectric Constant (DK) / Dissipation Factor (DF) Table

Core Data

Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
		2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
0.02	0.508	2.80 0.0025	2.80 0.0025	2.80 0.0025	2.80 0.0025	2.80 0.0025
0.03	0.762	2.80 0.0025	2.80 0.0025	2.80 0.0025	2.80 0.0025	2.80 0.0025
0.06	1.524	2.80 0.0025	2.80 0.0025	2.80 0.0025	2.80 0.0025	2.80 0.0025
0.02	0.508	3.00 0.003	3.00 0.003	3.00 0.003	3.00 0.003	3.00 0.003
0.03	0.762	3.00 0.003	3.00 0.003	3.00 0.003	3.00 0.003	3.00 0.003
0.06	1.524	3.00 0.003	3.00 0.003	3.00 0.003	3.00 0.003	3.00 0.003
0.02	0.508	3.20 0.003	3.20 0.003	3.20 0.003	3.20 0.003	3.20 0.003
0.03	0.762	3.20 0.003	3.20 0.003	3.20 0.003	3.20 0.003	3.20 0.003
0.06	1.524	3.20 0.003	3.20 0.003	3.20 0.003	3.20 0.003	3.20 0.003
0.02	0.508	3.33 0.003	3.33 0.003	3.33 0.003	3.33 0.003	3.33 0.003
0.03	0.762	3.33 0.003	3.33 0.003	3.33 0.003	3.33 0.003	3.33 0.003
0.06	1.524	3.33 0.003	3.33 0.003	3.33 0.003	3.33 0.003	3.33 0.003

Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
		2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
0.02	0.508	3.38 0.0035	3.38 0.0035	3.38 0.0035	3.38 0.0035	3.38 0.0035
0.03	0.762	3.38 0.0035	3.38 0.0035	3.38 0.0035	3.38 0.0035	3.38 0.0035
0.06	1.524	3.38 0.0035	3.38 0.0035	3.38 0.0035	3.38 0.0035	3.38 0.0035
0.02	0.508	3.45 0.0035	3.45 0.0035	3.45 0.0035	3.45 0.0035	3.45 0.0035
0.03	0.762	3.45 0.0035	3.45 0.0035	3.45 0.0035	3.45 0.0035	3.45 0.0035
0.06	1.524	3.45 0.0035	3.45 0.0035	3.45 0.0035	3.45 0.0035	3.45 0.0035

NOTE

Please Contact us for more details in below details.

Isola Group 3100 West Ray Road

Suite 301

Chandler, AZ 85226

Phone: 480-893-6527

Phone: 800-537-7656

Fax: 480-893-1409