

Dielectric Constant (DK) / Dissipation Factor (DF) Table

Core Data

Construction	Resin Content %	Weave Type	Offering	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)					
						1 GHz	2 Ghz	5 Ghz	10 GHz	15 Ghz	20 Ghz
1x1067	66.5%	Spread	Standard	0.0020	0.051	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017
1x1035	73.5%	Spread	Standard	0.0025	0.064	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014
1x1078	66.0%	Spread	Standard	0.0030	0.076	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018
1x1078	70.5%	Spread	Standard	0.0035	0.089	3.02 0.0015	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.01 0.0016
2x1035	67.5%	Spread	Alternate	0.0040	0.102	3.07 0.0017	3.07 0.0017	3.07 0.0017	3.07 0.0017	3.07 0.0017	3.07 0.0017
1x3313	58.5%	Open	Standard	0.0040	0.102	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022
2x1067	66.5%	Spread	Standard	0.0040	0.102	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017
2x1067	70.0%	Spread	Standard	0.0045	0.114	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016
2x1078	60.0%	Spread	Standard	0.0050	0.127	3.19 0.0021	3.19 0.0021	3.19 0.0021	3.19 0.0021	3.19 0.0021	3.19 0.0021
1x3313	66.0%	Open	Alternate	0.0050	0.127	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018
2x1067	72.5%	Spread	Standard	0.0050	0.127	2.98 0.0014	2.98 0.0014	2.98 0.0015	2.98 0.0015	2.98 0.0015	2.98 0.0015
2x1078	66.0%	Spread	Standard	0.0060	0.152	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018

Construction	Resin Content %	Weave Type	Offering	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)					
						1 GHz	2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
2x1078	70.5%	Spread	Standard	0.0070	0.178	3.02 0.0015	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.01 0.0016
2x3313	58.5%	Open	Standard	0.0080	0.203	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022
2x3313	63.5%	Open	Alternate	0.0090	0.229	3.16 0.0020	3.16 0.0020	3.16 0.0020	3.16 0.0020	3.16 0.0020	3.16 0.0020
3x1078	68.5%	Spread	Standard	0.0100	0.254	3.04 0.0016	3.04 0.0016	3.04 0.0016	3.04 0.0016	3.04 0.0016	3.04 0.0016
2x3313	66.0%	Open	Alternate	0.0100	0.254	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018
3x3313	58.5%	Open	Standard	0.0120	0.305	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022	3.24 0.0022
2x3313/1078	66.5%	Open	Alternate	0.0133	0.338	3.10 0.0018	3.10 0.0018	3.10 0.0018	3.10 0.0018	3.10 0.0018	3.10 0.0018
3x3313	62.5%	Open	Standard	0.0140	0.356	3.15 0.0020	3.15 0.0020	3.15 0.0020	3.15 0.0020	3.15 0.0020	3.15 0.0020
4x2116	57.0%	Open	Standard	0.0200	0.508	3.25 0.0022	3.25 0.0022	3.25 0.0022	3.25 0.0022	3.25 0.0022	3.25 0.0022

Dielectric Constant (DK) / Dissipation Factor (DF) Table

Prepreg Data

Glass Style	Resin Content %	Weave Type	Offering	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)					
						1 GHz	2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
1035	69.0%	Spread	Standard	0.0020	0.051	3.06 0.0017	3.06 0.0017	3.06 0.0017	3.06 0.0017	3.06 0.0017	3.06 0.0017
1067	70.0%	Spread	Standard	0.0022	0.056	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017	3.05 0.0017
106	76.0%	Open	Standard	0.0023	0.058	2.95 0.0013	2.95 0.0013	2.95 0.0014	2.95 0.0014	2.95 0.0014	2.95 0.0014
1067	71.5%	Spread	Standard	0.0024	0.061	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016
1035	75.0%	Spread	Standard	0.0026	0.066	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014
1067	74.0%	Spread	Standard	0.0026	0.066	2.98 0.0014	2.98 0.0014	2.98 0.0015	2.98 0.0015	2.98 0.0015	2.98 0.0015
1067	76.5%	Spread	Standard	0.0029	0.074	2.94 0.0013	2.94 0.0013	2.94 0.0013	2.94 0.0013	2.94 0.0013	2.94 0.0013
1078	65.0%	Spread	Standard	0.0029	0.074	3.14 0.0019	3.14 0.0019	3.14 0.0019	3.14 0.0019	3.14 0.0019	3.14 0.0019
1078	67.5%	Spread	Standard	0.0031	0.079	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018	3.09 0.0018
1078	70.5%	Spread	Standard	0.0035	0.089	3.04 0.0016	3.04 0.0016	3.04 0.0016	3.04 0.0016	3.04 0.0016	3.04 0.0016
1080	72.0%	Open	Standard	0.0038	0.097	3.02 0.0015	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.01 0.0016
1078	72.0%	Spread	Standard	0.0037	0.094	3.02 0.0015	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.02 0.0016	3.01 0.0016

Glass Style	Resin Content %	Weave Type	Offering	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)					
						1 GHz	2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
1078	75.0%	Spread	Standard	0.0042	0.107	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014
1080	75.0%	Open	Standard	0.0043	0.109	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014	2.97 0.0014
1080	78.0%	Open	Alternate	0.0046	0.117	2.92 0.0013	2.92 0.0013	2.92 0.0014	2.92 0.0014	2.92 0.0014	2.92 0.0014
1078	78.0%	Spread	Alternate	0.0046	0.117	2.92 0.0013	2.92 0.0013	2.92 0.0014	2.92 0.0014	2.92 0.0014	2.92 0.0014
3313	63.5%	Open	Standard	0.0046	0.117	3.16 0.0020	3.16 0.0020	3.16 0.0020	3.16 0.0020	3.16 0.0020	3.16 0.0020
3313	66.5%	Open	Standard	0.0051	0.129	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018	3.11 0.0018
2116	62.0%	Open	Standard	0.0058	0.147	3.19 0.0021	3.19 0.0021	3.19 0.0021	3.19 0.0021	3.19 0.0021	3.19 0.0021
2116	65.0%	Open	Alternate	0.0064	0.163	3.14 0.0019	3.14 0.0019	3.14 0.0019	3.14 0.0019	3.14 0.0019	3.14 0.0019

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. Tachyon[®] 100G is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.
© 2016, Isola Group, All rights reserved.



NOTE

Revisions:

A - Original-4/17

B - Adjusted prepreg thickness values-6/18

C - Added Standard & Alternate construction-8/18;

D - Added 9 mil core 5/19

E - Optimized construction set 6/19

F - Clarified Weave and Offering, eliminated low Frequency data 1/20

Standard-Commonly available; Alternate-Available, but not stocked