



185HR

185HR is a proprietary, high performance resin system with a Tg of 180°C (by DSC) for multilayer Printed Wiring Board (PWB) applications where maximum thermal performance and reliability are required.

185HR laminate and prepreg products are manufactured using Isola's patented technology, reinforced with electrical grade (E-glass) glass fabric. This system delivers a 340°C decomposition temperature, a lower Z-axis expansion and offers lower loss compared to competitive products in this space.

The 185HR system is also laser fluorescing and UV blocking for maximum compatibility with Automated Optical Inspection (AOI) systems, optical positioning systems and photoimageable solder mask imaging.

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2
D-52348 Düren, Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

Performance

Tg 180°C

Td 340°C

Dk 4.01

Df 0.0200

zIPC- 4101C /21 /24 /26 /98 /101 /126

UL - File Number E41625

Qualified to UL's MCIL Program

Product Features

- Processing Advantages

Product Availability

- Available in full size sheet or panel form
- Roll or panel form
- Glass Fabric Availability

185HR Specifications

Property		Typical Values			
		Typical Value	Specification	Units	Test Method
				Metric (English)	IPC-TM-650 (or as noted)
Test data generated from		45	—	%	2.3.16.2
Glass Transition Temperature (Tg) by DSC		180	170-200	°C	2.4.25
Glass Transition Temperature (Tg) by DMA		185	170-200	°C	2.4.25
Decomposition Temperature (Td) by TGA @ 5% weight loss		340	—	°C	
		60	—		
		>15	—		
Test data generated from	A. Post-Tg	40	AABUS		2.4.24
	B. Pre-Tg	220	—		
	A. Pre-Tg	13/14	AABUS		2.4.24
	B.	14/17	—		
		2.7	—	%	2.4.24
Thermal Conductivity		0.4	—	W/mK	
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched	Pass	Pass Visual		2.4.13.1
	B. Etched				
Test data generated from	A.	4.13	5.4	-	2.5.17.1
	B.	4.04	—	-	
	C.	4.01	—	-	
	D.	3.88	—	-	
	E.	3.88	—	-	
	F.	0.0158	5.4	-	
	G.	0.0192	—	-	
	H.	0.0200	—	-	
	I.	0.0235	—	-	
	J.	0.0236	—	MΩ-cm	
Volume Resistivity	A.	—	1.0x106		2.5.17.1
	B. After moisture resistance	3.0x108	—	MΩ-cm	
	C. At elevated temperature	7.0x108	1.0x103		
Surface Resistivity	A.	—	1.0x106		2.5.17.1
	B. After moisture resistance	3.0x106	—	MΩ	
	C. At elevated temperature	2.0x108	1.0x103		
Dielectric Breakdown		>50	—	kV	2.5.6
Arc Resistance		115	60	Seconds	2.5.1
		54 (1350)	30 (750)		
Comparative Tracking Index (CTI)		3 (175-249)	—	Class (Volts)	
Peel Strength	A.	0.969 (5.5)	0.70 (4.0)		2.4.8.3 2.4.4
	B. Standard profile copper	—	—		
	1. After thermal stress				
	2. After thermal stress	1.06 (5.9)	0.80 (4.5)		
	3. At 125°C (257°F)	1.06 (5.9)	0.70 (4.0)		
	4. After process solutions	0.969 (5.5)	0.55 (3.5)		
Flexural Strength	A.	97,100		lb/inch2	2.4.4
	B.	54,100	—		
Tensile Strength	A.	53,337		lb/inch2	
	B.	35,678	—		
Test data generated from	A.	3770	—	-	
	B.	3337			
Poisson's Ratio	A.	0.172	—	-	
	B.	0.155			
Moisture Absorption		0.15	—	%	2.6.2.1
Test data generated from		V-0	—	°C	
Max Operating Temperature		130	UL Cert	°C	

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

isola.keostaging.com/products/printed-circuit-materials/185hr-laminate-materials/

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. 185HR is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.

isola