

Dielectric Constant(Dk) / Dissipation factor (Df) Table Core Data

Constructions	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)					
				100 MHz	500 MHz	1 GHz	2 GHz	5 GHz	10 GHz
1x 106	71.00%	0.0019	0.048	4.03 0.0160	3.99 0.0170	3.95 0.0190	3.91 0.0200	3.86 0.0220	3.81 0.0220
1x 1067	76.00%	0.0029	0.074	3.95 0.0160	3.91 0.0170	3.87 0.0190	3.83 0.0200	3.78 0.0220	3.73 0.0220
1x 1080	67.00%	0.0033	0.084	4.09 0.0150	4.05 0.0160	4.01 0.0180	3.97 0.0190	3.92 0.0210	3.87 0.0210
2x 106	71.00%	0.0038	0.097	4.03 0.0160	3.99 0.0170	3.95 0.0190	3.91 0.0200	3.86 0.0220	3.81 0.0220
1x 1080	72.00%	0.004	0.102	4.01 0.0160	3.97 0.0170	3.93 0.0190	3.89 0.0200	3.84 0.0220	3.79 0.0220
1x 2113	60.00%	0.0044	0.112	4.21 0.0140	4.17 0.0150	4.13 0.0170	4.09 0.0180	4.04 0.0200	3.99 0.0200
1x 1080	76.00%	0.0045	0.114	3.95 0.0160	3.91 0.0170	3.87 0.0190	3.83 0.0200	3.78 0.0220	3.73 0.0220
2x 106	74.00%	0.0046	0.117	3.98 0.0160	3.94 0.0170	3.90 0.0190	3.86 0.0200	3.81 0.0220	3.76 0.0220
1x 2116	57.00%	0.005	0.127	4.27 0.0140	4.23 0.0150	4.19 0.0170	4.15 0.0180	4.10 0.0200	4.05 0.0200

Prepreg Dielectric Constant(Dk)/Dissipation factor (Df) Table Prepreg Data

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)					
				100 MHz	500 MHz	1 GHz	2 GHz	5 GHz	10 GHz
106	71.00%	0.0019	0.048	4.03 0.0160	3.99 0.0170	3.95 0.0190	3.91 0.0200	3.86 0.0220	3.81 0.0220
1027	77.00%	0.002	0.051	3.95 0.0160	3.91 0.0170	3.87 0.0190	3.83 0.0200	3.78 0.0220	3.73 0.0220
106	77.00%	0.0027	0.069	3.95 0.0150	3.91 0.0160	3.87 0.0180	3.83 0.0190	3.78 0.0210	3.73 0.0210
1067	71.00%	0.0028	0.071	4.03 0.0160	3.99 0.0170	3.95 0.0190	3.91 0.0200	3.86 0.0220	3.81 0.0220
1067	76.00%	0.0029	0.074	3.95 0.0160	3.91 0.0170	3.87 0.0190	3.83 0.0200	3.78 0.0220	3.73 0.0220
1080	67.00%	0.0033	0.084	4.09 0.0140	4.05 0.0150	4.01 0.0170	3.97 0.0180	3.92 0.0200	3.87 0.0200
1078	69.50%	0.0035	0.089	4.05 0.0160	4.01 0.0170	3.97 0.0190	3.93 0.0200	3.88 0.0220	3.83 0.0220
1078	73.00%	0.0039	0.099	3.99 0.0160	3.95 0.0170	3.91 0.0190	3.87 0.0200	3.82 0.0220	3.77 0.0220
1080	72.00%	0.004	0.102	4.01 0.0140	3.97 0.0150	3.93 0.0170	3.89 0.0180	3.84 0.0200	3.79 0.0200



370HR ULTRA

Industry Leading, Very Low CTE, Epoxy Laminate and Prepreg

Revision No: A | October 21, 2026

NOTE

Revisions:

A. Initial Release 10/21/2026

Isola, the Isola logo, The Base for Innovation, Astra, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Tachyon, and TerraGreen are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2026 Isola Group. All rights reserved.