

Dielectric Constant (DK) / Dissipation Factor (DF) Table

Core Data

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
				2 Ghz	5 Ghz	10 GHz	15 Ghz	20 Ghz
1x1037	73.0%	0.0020	0.051	3.10 0.0025	3.10 0.0026	3.10 0.0026	3.10 0.0026	3.10 0.0026
1x1067	70.0%	0.0025	0.064	3.25 0.0027	3.25 0.0028	3.25 0.0028	3.25 0.0028	3.24 0.0028
1x1078	63.0%	0.0030	0.076	3.40 0.0031	3.40 0.0032	3.40 0.0032	3.40 0.0032	3.40 0.0032
1x1078	67.0%	0.0035	0.089	3.30 0.0029	3.30 0.0030	3.30 0.0030	3.30 0.0030	3.30 0.0030
1x3313	54.0%	0.0040	0.102	3.60 0.0037	3.60 0.0037	3.60 0.0037	3.60 0.0037	3.60 0.0037
2x1037	73.0%	0.0043	0.109	3.10 0.0025	3.10 0.0026	3.10 0.0026	3.10 0.0026	3.10 0.0026
2x1067	67.0%	0.0045	0.114	3.31 0.0029	3.31 0.0030	3.31 0.0030	3.31 0.0030	3.31 0.0030
1x3313	58.0%	0.0045	0.114	3.50 0.0034	3.50 0.0035	3.50 0.0035	3.50 0.0035	3.50 0.0035
2x1067	70.0%	0.0050	0.127	3.54 0.0027	3.54 0.0028	3.54 0.0028	3.54 0.0028	3.54 0.0028
1x3313	62.0%	0.0050	0.127	3.42 0.0032	3.42 0.0033	3.42 0.0033	3.42 0.0033	3.42 0.0033
1x2116	54.0%	0.0050	0.127	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037
2x1078	60.0%	0.0055	0.140	3.48 0.0035	3.48 0.0035	3.48 0.0035	3.48 0.0035	3.48 0.0035

Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
				2 Ghz	5 Ghz	10 GHz	15 Ghz	20 Ghz
1x2116	57.0%	0.0055	0.140	3.54 0.0033	3.54 0.0034	3.54 0.0034	3.54 0.0034	3.54 0.0034
1x2116	60.0%	0.0060	0.152	3.47 0.0033	3.47 0.0034	3.47 0.0034	3.47 0.0034	3.47 0.0034
2x1078	63.0%	0.0062	0.157	3.40 0.0031	3.40 0.0032	3.40 0.0032	3.40 0.0032	3.40 0.0032
2x1078	67.0%	0.0070	0.178	3.30 0.0029	3.30 0.0030	3.30 0.0030	3.30 0.0030	3.30 0.0030
2x1078	69.3%	0.0076	0.193	3.27 0.0027	3.27 0.0028	3.27 0.0028	3.27 0.0028	3.27 0.0028
2x3313	54.0%	0.0080	0.203	3.60 0.0037	3.60 0.0037	3.60 0.0037	3.60 0.0037	3.60 0.0037
2x3313	58.0%	0.0090	0.229	3.50 0.0034	3.50 0.0035	3.50 0.0035	3.50 0.0035	3.50 0.0035
2x3313	62.0%	0.0100	0.254	3.42 0.0032	3.42 0.0033	3.42 0.0033	3.42 0.0033	3.42 0.0033
2x2116	54.0%	0.0100	0.254	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037
3x3313	54.0%	0.0120	0.305	3.60 0.0037	3.60 0.0037	3.60 0.0037	3.60 0.0037	3.60 0.0037
2x3313/1078	61.5%	0.0130	0.330	3.42 0.0031	3.42 0.0032	3.42 0.0032	3.42 0.0032	3.42 0.0032
2x3313/1078	62.5%	0.0132	0.335	3.41 0.0031	3.41 0.0032	3.41 0.0032	3.41 0.0032	3.41 0.0032
2x3313/1078	64.5%	0.0140	0.356	3.37 0.0031	3.37 0.0031	3.37 0.0031	3.36 0.0031	3.36 0.0031
3x3313	64.5%	0.0150	0.381	3.42 0.0032	3.42 0.0033	3.42 0.0033	3.42 0.0033	3.42 0.0033
3x2116	54.0%	0.0150	0.381	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037
2x1078/2x3313	62.4%	0.0160	0.406	3.42 0.0031	3.42 0.0032	3.42 0.0032	3.42 0.0032	3.42 0.0032

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. TerraGreen® is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners. © 2016, Isola Group, All rights reserved.



Construction	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
				2 Ghz	5 Ghz	10 GHz	15 Ghz	20 Ghz
2x1078/2x3313	63.6%	0.0166	0.422	3.39 0.0032	3.39 0.0032	3.39 0.0032	3.39 0.0032	3.39 0.0032
4x3313	58.0%	0.0180	0.457	3.50 0.0034	3.50 0.0035	3.50 0.0035	3.50 0.0035	3.50 0.0035
4x3313	62.0%	0.0200	0.508	3.42 0.0032	3.42 0.0033	3.42 0.0033	3.42 0.0033	3.42 0.0033
4x2116	54.0%	0.0200	0.508	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037	3.61 0.0037

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. TerraGreen® is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners. © 2016, Isola Group, All rights reserved.



Dielectric Constant (DK) / Dissipation Factor (DF) Table

Prepreg Data

Glass Style	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
				2 Ghz	5 Ghz	10 GHz	15 Ghz	20 Ghz
1037	73.0%	0.0022	0.056	3.18 0.0025	3.18 0.0026	3.18 0.0026	3.18 0.0026	3.18 0.0026
106	73.0%	0.0023	0.058	3.18 0.0025	3.18 0.0026	3.18 0.0026	3.18 0.0026	3.18 0.0026
1067	70.0%	0.0025	0.064	3.25 0.0027	3.25 0.0028	3.25 0.0028	3.25 0.0028	3.24 0.0028
1078	60.0%	0.0028	0.071	3.47 0.0033	3.47 0.0034	3.47 0.0034	3.47 0.0034	3.47 0.0034
1067	73.0%	0.0029	0.074	3.18 0.0025	3.18 0.0026	3.18 0.0026	3.18 0.0026	3.18 0.0026
1078	63.0%	0.0031	0.079	3.40 0.0031	3.40 0.0032	3.40 0.0032	3.40 0.0032	3.40 0.0032
1078	67.0%	0.0035	0.089	3.31 0.0029	3.31 0.0030	3.31 0.0030	3.31 0.0030	3.31 0.0030
1080	68.0%	0.0036	0.091	3.29 0.0028	3.29 0.0029	3.29 0.0029	3.29 0.0029	3.29 0.0029
1080	71.0%	0.0040	0.102	3.22 0.0027	3.22 0.0027	3.22 0.0027	3.22 0.0027	3.22 0.0027
1078	71.0%	0.0041	0.104	3.22 0.0027	3.22 0.0027	3.22 0.0027	3.22 0.0027	3.22 0.0027
3313	58.0%	0.0045	0.114	3.50 0.0034	3.50 0.0035	3.50 0.0035	3.50 0.0035	3.50 0.0035
3313	62.0%	0.0051	0.130	3.42 0.0032	3.42 0.0033	3.42 0.0033	3.42 0.0033	3.42 0.0033

Glass Style	Resin Content %	Thickness (inch)	Thickness (mm)	Dielectric Constant (DK) / Dissipation Factor (DF)				
				2 Ghz	5 Ghz	10 GHz	15 Ghz	20 Ghz
3313	65.0%	0.0056	0.142	3.35 0.0030	3.35 0.0031	3.35 0.0031	3.35 0.0031	3.35 0.0031
2116	57.0%	0.0056	0.142	3.54 0.0035	3.54 0.0035	3.54 0.0035	3.54 0.0035	3.54 0.0035
2116	60.0%	0.0061	0.155	3.47 0.0033	3.47 0.0034	3.47 0.0034	3.47 0.0034	3.47 0.0034

NOTE

Revisions:

A-Original-4/17

B-Adjusted 16.8 mil thickness to 16.6 mil thickness -12/19

All TerraGreen glass is Spread Weave in both directions

Standard-Commonly available

Alternate-Available, but not stocked