



DE104

Low Tg Laminate and Prepreg

DE104 offers excellent thermal resistance, due to its special resin system and a low coefficient of thermal expansion in the Z-axis.

The glass transition temperature (T_g) is 135°C (DSC). Time to delamination of the laminate at a temperature of 260°C is 12 minutes and the decomposition temperature (T_d) is 315°C. The product is listed as FR-4 and can be processed using standard parameters. DE104 multilayer (ML) corresponds to NEMA-grade FR-4 and meets the requirements of IPC-4101D WAM1.

Product Attributes

Legacy Materials

Typical Market Applications

Automotive & Transportation

ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group
6565 West Frye Road
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific
(Hong Kong) Ltd.
12/F, Kin Sang
Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH
Isola Strasse 2
D-52348 Düren,
Germany
Phone: 49-2421-8080
Fax: 49-2421-808164

Data Sheet

T_g 135°C

T_d 315°C

D_k 4.37

D_f 0.022

IPC-4101 - / 21

UL - File Number E41625

Last Updated June 24, 2020
Revision No: D

Product Features

- Industry Recognition
 - UL File Number: E41625
 - Qualified to UL's MCIL Program
 - RoHS Compliant
- Performance Attributes
- Processing Advantages
 - UV blocking and AOI fluorescence

Product Availability

- Standard Material Offering: Laminate
 - 2 to 93 mil (0.05 to 2.4 mm)
 - Available in full size sheet or panel form
- Copper Foil Type
 - HTE Grade 3
 - RTF (Reverse Treat Foil)
- Copper Weight
 - ½ to 2 oz (18 to 70 µm) available
 - Heavier copper available
 - Thinner copper foil available
- Standard Material Offering: Prepreg
 - Roll or panel form
 - Tooling of prepreg panels
- Glass Fabric Availability
 - E-glass
 - Square weave glass
 - Mechanically spread glass

DE104 Typical Values

Last Updated Jun 24, 2020

Property	Typical Value	Units	Test Method
		Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC	135	°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss	315	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	°C Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	ppm/°C	2.4.24C
Thermal Conductivity	0.36	W/mK	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual 2.4.13.1
Dk, Permittivity	A. @ 100 MHz B. @ 500 MHz C. @ 1 GHz D. @ 2 GHz E. @ 5 GHz	—	2.5.5.3 2.5.5.3 2.5.5.9 2.5.5.5 2.5.5.5
Df, Loss Tangent	A. @ 100 MHz B. @ 500 MHz C. @ 1 GHz D. @ 2 GHz E. @ 5 GHz	—	2.5.5.3 2.5.5.3 2.5.5.9 2.5.5.5 2.5.5.5
Volume Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 1.3×10^6 3.4×10^7	MQ-cm 2.5.17.1
Surface Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 1.0×10^6 7.2×10^6	MQ 2.5.17.1
Dielectric Breakdown	>50	kV	2.5.6B
Arc Resistance	105	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)	54 (1350)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)	2	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 µm [0.669 mil] B. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	1.23 (7.0) 1.58 (9.0) 1.23 (7.0) 1.58 (9.0)	2.4.8C N/mm (lb/inch) 2.4.8.2A 2.4.8.3 2.4.8.3
Flexural Strength	A. Length direction B. Cross direction	84.0 65.2	ksi 2.4.4B
Tensile Strength	A. Length direction B. Cross direction	57.0 42.4	ksi ASTM D3039
Moisture Absorption	0.3	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)	V-0	Rating	UL 94
Relative Thermal Index (RTI)	130	°C	UL 796

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

<https://www.isola-group.com/products/all-printed-circuit-materials/de104/>

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. DE104 is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2020, Isola Group, All rights reserved.



NOTE

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected 5 GHz Df label

C: Corrected units for Flexural and Tensile Strength - 8/18

D: Change MOT to RTI 5/19