

Dielectric Constant(Dk) / Dissipation factor (Df) Table

Core Data

Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)				
		2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
0.005	0.127	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028
0.010	0.254	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028
0.020	0.508	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028
0.030	0.762	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028
0.040	1.016	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028
0.060	1.524	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028	3.38 0.0028
0.005	0.127	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030
0.0066	0.168	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030
0.010	0.254	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030
0.020	0.508	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030
0.030	0.762	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030
0.060	1.524	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030	3.45 0.0030
0.005	0.127	3.60 0.0032	3.60 0.0032	3.60 0.0032	3.60 0.0032	3.60 0.0032
0.010	0.254	3.60 0.0032	3.60 0.0032	3.60 0.0032	3.60 0.0032	3.60 0.0032
0.020	0.508	3.60 0.0032	3.60 0.0032	3.60 0.0032	3.60 0.0032	3.60 0.0032
0.010	0.254	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033
0.0133	0.338	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033
0.020	0.508	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033



I-Tera® MT40 (RF/MW)

Very Low-Loss Laminate

Revision No: B | February 1, 2025

0.030	0.762	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033	3.75 0.0033
-------	-------	----------------	----------------	----------------	----------------	----------------

Prepreg Dielectric Constant(Dk) / Dissipation factor (Df) Table

Prepreg Data

Glass Style	Resin content %	Dielectric Constant (DK)/ Dissipation Factor (DF)					
		Thickness (inch)	Thickness (mm)	2 GHz	5 GHz	10 GHz	20 GHz

NOTE

Revisions:

A-Original Release - 4/17

B-Added 10 mil 3.60 Dk and 30 mil 3.45 Dk - 2/20

Isola, the Isola logo, The Base for Innovation, Astra, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Tachyon, and TerraGreen are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2023 Isola Group. All rights reserved.