isola

# I-Tera® MT40 (RF/MW)

Very Low Loss Laminate Material

Tg 200°C Td 390°C Dk 3.38 / 3.46 / 3.46 ; 3.78 Df 0.0028 / 0.0031

I-Tera® MT40 laminate materials exhibit exceptional electrical properties which are very stable over a broad frequency and temperature range.