



I-Tera MT40

I-Tera® MT40 laminate materials exhibit exceptional electrical properties which are very stable over a broad frequency and temperature range.

I-Tera MT40 is suitable for many of today's high speed digital and RF/microwave printed circuit designs. I-Tera MT40 features a dielectric constant (Dk) that is stable between -55°C and +125°C up to W-band frequencies. In addition, I-Tera MT40 offers a lower dissipation factor (Df) of 0.0031 making it a cost effective alternative to PTFE and other commercial microwave and high-speed digital laminate materials.

I-Tera MT40 laminate materials are currently being offered in both laminate and prepreg form in typical thicknesses and standard panel sizes. This provides a complete materials solution package for high-speed digital multilayer, hybrid, RF/microwave, multilayer and double-sided printed circuit designs. I-Tera MT40 does not require any special through hole treatments commonly needed when processing PTFE-based laminate materials.

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2
D-52348 Düren, Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

Performance

Tg 200°C

Td 360°C

Dk 3.45

Df 0.0031

zIPC- 4101C /21 /24 /26 /98 /101 /126

UL - File Number E41625

Qualified to UL's MCIL Program

Product Features

- Industry Recognition
 - UL File Number: E41625
 - RoHS Compliant
- Performance Attributes
- Processing Advantages

Product Availability

- Standard Material Offering: Laminate
 - 2 to 18 mil (0.5 to 0.46 mm)
 - Available in full size sheet or panel form
- Copper Foil Type
 - HTE Grade 3
 - VLP-2 (2 micron), 1 oz and below
 - RTF (Reverse Treat Foil)
- Copper Weight
 - ½ to 2 oz (18 to 70 µm) available
 - Heavier copper available
 - Thinner copper foil available
- Standard Material Offering: Prepreg
 - Roll or panel form
 - Tooling of prepreg panels
- Glass Fabric Availability
 - Square weave glass
 - Mechanically spread glass

I-Tera MT40 Specifications

Property		Typical Value	Units	Test Method
			Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC		200	°C	2.4.25
Glass Transition Temperature (Tg) by TMA		205	°C	2.4.24
Decomposition Temperature (Td) by TGA @ 5% weight loss		360	°C	2.4.24.2
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	>60	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	55 290 2.8	ppm/°C ppm/°C %	2.4.24
X/Y-Axis CTE	Pre-Tg	12	ppm/°C	2.4.24.1
Thermal Conductivity		0.61	W/mK	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 1 GHz B. @ 2 GHz C. @ 5 GHz D. @ 10 GHz	—	—	Bereskin Stripline
Df, Loss Tangent	A. @ 1 GHz B. @ 2 GHz	—	—	Bereskin Stripline
Dk, Permittivity	A. @ 5 GHz B. @ 10 GHz	—	—	Bereskin Stripline
Volume Resistivity	C-96/35/90	1.33×10^7	MΩ-cm	2.5.17.1
Surface Resistivity	C-96/35/90	1.33×10^5	MΩ	2.5.17.1
Dielectric Breakdown		45.4	kV	2.5.6
Arc Resistance		139	Seconds	2.5.1
Electric Strength (Laminate & laminated prepreg)		45 (1133)	kV/mm (V/mil)	2.5.6.2
Comparative Tracking Index (CTI)		2	Class (Volts)	UL 746A ASTM D3638
Peel Strength	1 oz. EDC foil	1.0 (5.7)	N/mm (lb/inch)	2.4.8
Flexural Strength	A. Length direction B. Cross direction	71000 58000	lb/inch ²	2.4.4
Tensile Strength	A. Length direction B. Cross direction	39000 35000	lb/inch ²	ASTM D3039
Poisson's Ratio	A. Length direction B. Cross direction	0.234 0.222	—	ASTM D3039
Moisture Absorption		0.1	%	2.6.2.1
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Max Operating Temperature		130	°C	UL 796

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

isola.keostaging.com/products/printed-circuit-materials/product-template-copy-22/

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. I-Tera MT40 is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.

isola

Last Updated Aug 2, 2016