



DE156

DE156 is a base material of type FR-4. The resin matrix is based on a modified epoxy resin; conventional E-glass-fabric is used for reinforcement.

The requirements of flammability class V-0 as per UL 94 are met without addition of antimony compounds. Since this grade does not contain halogens, it displays greater thermal stability than a standard FR-4, as time to delamination (T260) measurements prove.

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2
D-52348 Düren, Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

Performance

Tg 155°C

Td 390°C

Dk 4.00

Df 0.02

zIPC- 4101C /21 /24 /26 /98 /101 /126

UL - File Number E41625

Qualified to UL's MCIL Program

Product Features

- Industry Recognition
 - UL File Number: E41625
 - RoHS Compliant
- Performance Attributes
 - Halogen free
- Processing Advantages
 - UV blocking and AOI fluorescence

Product Availability

- Standard Material Offering: Laminate
 - 2 to 60 mil (0.5 to 1.5 mm)
 - Available in full size sheet or panel form
- Copper Foil Type
 - HTE Grade 3
 - RTF (Reverse Treat Foil)
- Copper Weight
 - ½ to 2 oz (18 to 70 µm) available
 - Heavier copper available
 - Thinner copper foil available
- Standard Material Offering: Prepreg
 - Roll or panel form
 - Tooling of prepreg panels
- Glass Fabric Availability
 - E-glass
 - Square weave glass

DE156 Specifications

Property		Typical Value	Units	Test Method
			Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC		155	°C	2.4.25
Decomposition Temperature (Td) by TGA @ 5% weight loss		390	°C	2.4.24.2
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	60 >10	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	45 220 2.8	ppm/°C ppm/°C %	2.4.24
X/Y-Axis CTE	Pre-Tg	133	ppm/°C	2.4.24.1
Thermal Conductivity		0.4	W/mK	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	4.05 4.01 4.00 3.97 —	—	2.5.5.3 Bereskin Stripline Bereskin Stripline Bereskin Stripline Bereskin Stripline
Df, Loss Tangent	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	0.0130 0.0161 0.0167 0.0172 0.0172	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Volume Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	5.0×10^6 3.0×10^7 2.8×10^6	MΩ-cm	2.5.17.1
Surface Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	2.0×10^3 4.0×10^6 1.0×10^7	MΩ	2.5.17.1
Dielectric Breakdown		60	kV	2.5.6
Arc Resistance		115	Seconds	2.5.1
Electric Strength (Laminate & laminated prepreg)		36 (1500)	kV/mm (V/mil)	2.5.6.2
Comparative Tracking Index (CTI)		—	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil]	7.0	N/mm (lb/inch)	2.4.8
	B. Standard profile copper	8.0		2.4.8.2
	1. After thermal stress	6.0		2.4.8.3
	2. At 125°C (257°F)	7.0		2.4.8.3
	3. After process solutions			
Flexural Strength	A. Length direction B. Cross direction	89,500 62,700	lb/inch ²	2.4.4
Tensile Strength	A. Length direction B. Cross direction	55,242 39,335	lb/inch ²	ASTM D3039
Poisson's Ratio	A. Length direction B. Cross direction	0.175 0.143	—	ASTM D3039
Moisture Absorption		0.1	%	2.6.2.1
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Max Operating Temperature		130	°C	UL 796

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

isola.keostaging.com/products/printed-circuit-materials/product-template-copy-4/

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. DE156 is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.

isola

Last Updated Aug 2, 2016