

UL - File Number E41625

TerraGreen® 400G laminate materials are our most advanced ultra high speed, halogen free ultra low loss design solution.

PRODUCT FEATURES

PRODUCT AVAILABILITY

TerraGreen® 400G is our Halogen Free material solution for next generation 5G infrastructure and computing applications. Our novel resin system has been engineered for high data rates with excellent cost for loss performance.

TerraGreen® 400G is lead free compatible and can be processed utilizing standard PCB equipment and processing steps.

TerraGreen® 400G meets UL 94 V-0 and is halogen free.

PRODUCT ATTRIBUTES



HALOGEN
FREE



HIGH SPEED
DIGITAL



HIGH THERMAL
RELIABILITY

TYPICAL MARKET APPLICATIONS



NETWORKING &
COMMUNICATIONS



AEROSPACE
& DEFENSE



COMPUTING, STORAGE
& PERIPHERALS

ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
AZ 85226 Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd. 12/F,
Kin Sang Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon,
Hong Kong Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
Germany Phone: 49-2421-8080
Fax: 49-2421-808164

Typical Values Table

Property		Typical Value	Units	Test Method
			Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DMA		210	—	2.4.24.4
Glass Transition Temperature (Tg) by TMA		180	°C	2.4.24C
Decomposition Temperature (Td) by TGA @ 5% weight loss		400	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	T288	60+	Minutes	2.4.24.1
Z-Axis CTE		2.8	ppm/°C	2.4.24C
X/Y-Axis CTE		14-23	ppm/°C	2.4.24C
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 5 GHz B. @ 10 GHz C. @ 20 GHz	3.05	—	Bereskin Stripline
Df, Loss Tangent	A. @ 5 GHz B. @ 10 GHz C. @ 20 GHz	0.0018	—	Bereskin Stripline
Peel Strength	Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil]	0.65 (3.9)	N/mm (lb/inch)	2.4.8C
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

NOTES

Notes:
All data is preliminary and subject to change
*** Data was developed using 55% RC rigid laminate**

Revisions:
A: Preliminary Release

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.