

IPC-4101 /134 UL - File Number E41625

TerraGreen® 400G laminate materials are our most advanced ultra high speed, halogen free ultra low loss design solution.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- RoHS Compliant

Performance Attributes

- CAF resistant
- Low moisture absorption
- Halogen free
- 6x 260°C reflow capable
- 6x 288°C solder float capable

Processing Advantages

- FR-4 process compatible
- Excellent Fill and Flow
- Multiple lamination cycles
- HDI technology compatible

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 2 to 10 mil (0.05 to 0.25 mm)

Copper Foil Type

- HVLP3 (VLP1) ≤1.1 micron Rz JIS
- Advanced RTF ≤2.5 micron Rz JIS

Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 µm) available
- Thinner copper foil available

Standard Material Offering: Prepreg

- Tooling of prepreg panels
- Moisture barrier packaging

Glass Fabric Availability

- Low Dk glass
- Square weave glass
- Mechanically spread glass

TerraGreen® 400G is our Halogen Free material solution for next generation 5G infrastructure, data center systems, high end computing, wired & wireless communications and AI applications. Our novel resin system, ultra smooth HVLP3(VLP1) copper foil and Low Dk glass has been engineered for very high data rates of >100 Gb/s with excellent cost for loss performance.

The TerraGreen® 400G resin system has proven superior CAF performance on tight pitch testing. CAF performance is enhanced by the resin systems excellent interlaminar and bond line adhesion strength.

TerraGreen® 400G is lead free compatible and sequential lamination capable and can be processed utilizing standard PCB equipment and processing steps. TerraGreen® 400G meets UL94 V-0.

PRODUCT ATTRIBUTES



TYPICAL MARKET APPLICATIONS



ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
AZ 85226 Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd.12/F,
Kin Sang Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon,
Hong Kong Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
Germany Phone: 49-2421-8080
Fax: 49-2421-808164

Typical Values Table

Property		Typical Value	Units	Test Method
			Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC		200	°C	2.4.25C
Glass Transition Temperature (Tg) by DMA		215	°C	2.4.24.4
Glass Transition Temperature (Tg) by TMA		180	°C	2.4.24C
Decomposition Temperature (Td) by TGA @ 5% weight loss		>380C	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T288 B. T300	60+	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	37 170 1.8	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE		12/13	ppm/°C	2.4.24C
Thermal Conductivity		0.54	W/m·K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 10 GHz B. @ 20 GHz	3.15 3.13	—	2.5.5.5
Df, Loss Tangent	A. @ 10 GHz B. @ 20 GHz	0.0017	—	2.5.5.5
Volume Resistivity	C-96/35/90	2.0x10 ⁸	MΩ-cm	2.5.17.1
Surface Resistivity	C-96/35/90	2.0x10 ⁷	MΩ	2.5.17.1
Dielectric Breakdown		70	kV	2.5.6B
Arc Resistance		180	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		67(1700)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		2 (250-499)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile and very low profile copper foil B. Low profile and very low profile copper foil ... After thermal stress	0.7 (4.1)	N/mm (lb/inch)	2.4.8C 2.4.8.2A
Flexural Strength	A. Length direction B. Cross direction	393 (57) 338 (49)	MPa (kpsi)	2.4.4B
Tensile Strength	A. Length direction B. Cross direction	220 (32) 193 (28)	MPa (kpsi)	ASTM D3039
Young's Modulus	A. Length direction B. Cross direction	14.5 (2100) 13.0 (1900)	GPa(kpsi)	ASTM D790-15e2
Flexural Modulus	A. Lengthwise B. Crosswise	12.1 (1750) 11.7 (1700)	GPa (kpsi)	ASTM D790-15e2
Poisson's Ratio	A. Length direction B. Cross direction	0.17 0.22	—	ASTM D3039
Moisture Absorption			%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		140	°C	UL 746

NOTES

Notes:

All data is preliminary and subject to change

*** Data was developed using 55% RC rigid laminate**

Revisions:

A: Preliminary Release B: Corrected Flexural Strength from 33 to 338 and units for Youngs Modulus from MPa to GPa - 1/24

C: Corrected laminate thickness offering from maximum 18 mils to 10 mils, updated copper foil offering - 3/24

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.