

Dielectric Constant(Dk) / Dissipation factor (Df) Table

Core Data

Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)				
		2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
0.0025	0.064	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018
0.0050	0.127	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018
0.0100	0.254	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018
0.0200	0.508	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018	3.15 0.0018

Prepreg Dielectric Constant(Dk) / Dissipation factor (Df) Table

Prepreg Data

Glass Style	Resin content %	Dielectric Constant (DK)/ Dissipation Factor (DF)					
		Thickness (inch)	Thickness (mm)	2 GHz	5 GHz	10 GHz	20 GHz



TerraGreen® 400G (RF/MW)

Halogen-free, Extremely Low Loss Material

NOTE

Revision No: A | October 20, 2025

Please Contact us for more details in below details.

Isola Group

3100 West Ray Road
Suite 301
Chandler, AZ 85226

Phone: 480-893-6527
Phone: 800-537-7656
Fax: 480-893-1409

Isola, the Isola logo, The Base for Innovation, Astra, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Tachyon, and TerraGreen are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2023 Isola Group. All rights reserved.